



TECHNICAL DATA SHEET

Compound :

NR

1,4 Cis-Polisoprene (92% minimo)

ORIGINAL PROPERTIES : Analysis on supplier laboratory compound

Physical-mechanical properties	Unit of measurement	Requested
Hardness	Shore A	30 ÷ 95
Density	g/cm ³	0,96 ÷ 1,55
Minimum temperature	° C	- 40 (- 50) **
Maximum temperature	° C	70 ÷ 90 **

Physical-mechanical characteristics	<p>Excellent mechanical properties (tensile strenght, elongation at break, tear resistance) even without the use of reinforcing fillers</p> <p>Resistance to permanent deformation under compression and tension from quite good to very good **</p> <p>Excellent abrasion resistance</p> <p>Rebound resistance from very good to excellent **</p>
--	--

Other properties	<p>Poor resistance to UV radiation</p> <p>Very good dielectric properties</p> <p>Quite good air and gas impermeability</p> <p>Any flame resistance</p> <p>Good dyeing</p>
-------------------------	--

Chemical compatibility	<p>Excellent in contact with:</p> <ul style="list-style-type: none"> - Water and saline solutions - Alcohols and glycols
	<p>Satisfactory in contact with:</p> <ul style="list-style-type: none"> - Water up to 70°C - Diluted acids and alkalis
	<p>Satisfactory enough in contact with:</p> <ul style="list-style-type: none"> - Acetone
	<p>Insufficient in contact with:</p> <ul style="list-style-type: none"> - Oils and mineral, animal, vegetable greases (except castor oil) - Aliphatic hydrocarbons and fuels - Aromatic and chlorinated hydrocarbons - Strong concentrated mineral acids - Atmospheric agents and ozone (except with formulations containing protective agents)

*depending from the types

** with a specific optimal formulation